

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
24 July 2003 (24.07.2003)

PCT

(10) International Publication Number
WO 03/059969 A1

(51) International Patent Classification⁷: **C08F 214/26**

(21) International Application Number: PCT/JP03/00330

(22) International Filing Date: 17 January 2003 (17.01.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/046,702 17 January 2002 (17.01.2002) US

(63) Related by continuation (CON) or continuation-in-part (CIP) to earlier application:

US 10/046,702 (CIP)
Filed on 17 January 2002 (17.01.2002)

(71) Applicant (for all designated States except US): **DAIKIN INDUSTRIES, LTD.** [JP/JP]; Umeda Center Bldg., 4-12, Nakazakinishi 2-chome, Kita-ku, Osaka-shi, Osaka 530-8323 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KONO, Hideki**

[JP/JP]; c/o DAIKIN INDUSTRIES, LTD., Yodogawa Plant., 1-1, Nishihitotsuya, Settsu-shi, Osaka 566-8585 (JP). **HIRAO, Takayuki** [JP/US]; c/o DAIKIN AMERICA, INC., 20 Olympic Drive, Orangeburg, NY 10962 (US). **GEORGE, Lin** [US/US]; c/o DAIKIN AMERICA, INC., 20 Olympic Drive, Orangeburg, NY 10962 (US). **FUKUDA, Kazuyuki** [JP/JP]; c/o DAIKIN INDUSTRIES, LTD., Yodogawa Plant., 1-1, Nishihitotsuya, Settsu-shi, Osaka 566-8585 (JP).

(74) Agents: **YASUTOMI, Yasuo** et al.; Chuo BLDG., 4-20, Nishinakajima 5-chome, Yodogawa-ku, Osaka-shi, Osaka 532-0011 (JP).

(81) Designated States (national): CN, US.

(84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FEP PELLET

(57) Abstract: An FEP pellet having a volatile content of 0.2 % by weight or less. The FEP pellet satisfies the following requirements (i) and (ii) when used to form an insulating material coating a core wire by extrusion coating at a coating speed of 2,800 ft/min.: (i) an adhesive strength between the insulating material and said core wire of 0.8 kg or more; and (ii) an average number of cone-breaks in the insulating material of one or less per 50,000 feet of the coated core wire.

501,978



WO 03/059969 A1